

	AP-5 PG 64-22		1621		2024-05-07 14:03
	620D504		RT2416214589		2024-05-01 21:00

, @15 kg/m ²	KSM 2002	1000	1044	
(15) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	356	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ((%)) %	KSM 2252	55	64	
%	KSM 2252	110	109	
(25)	KSM 2252	50 ~ 80	69	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	48.0	
@120 mm ² /s	ASTM D4402	To be reported	991.2	
@135 mm ² /s	ASTM D4402		450.3	
@150 mm ² /s	ASTM D4402	To be reported	229.1	
@180 mm ² /s	ASTM D4402	To be reported	77.2	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

K. W. Hwang

