

	AP-5 PG 64-22		1621		2024-06-03 08:50
	620D503		RT2416214597		2024-05-26 01:00

, @15 kg/m <sup>2</sup>	KSM 2002	1000	1041	
(15 ) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	358	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ( ( ) ) %	KSM 2252	55	63	
%	KSM 2252	110	110	
(25 )	KSM 2252	50 ~ 80	71	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	48.0	
@120 mm <sup>2</sup> /s	ASTM D4402	To be reported	978.1	
@135 mm <sup>2</sup> /s	ASTM D4402		439.5	
@150 mm <sup>2</sup> /s	ASTM D4402	To be reported	221.8	
@180 mm <sup>2</sup> /s	ASTM D4402	To be reported	74.0	
PG- (7 )	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

*K. W. Hwang*
