

	AP-5 PG 64-22		1621		2026-02-02 08:55
	520D121		RT2616214760		2026-01-03 01:30

, @15 kg/m ³	KSM 2002	1000	1043		
(15) cm	KSM 2254	100	140+		
,COC	KSM 2010	260	354		
FOAM ON HEAT,180	KSM 2201	NONE	NONE		
Loss on Heating wt%	KSM 2258	0.6	0.0		
가 ((%)) %	KSM 2252	55	65		
%	KSM 2252	110	103		
(25)	KSM 2252	50 ~ 80	65		
가 mass%	KSM 2201	99.0	99.9		
	KSM 2250	44.0 ~ 52.0	47.5		
@120 mm ² /s	ASTM D4402	To be reported	959.0		
@135 mm ² /s	ASTM D4402		434.7		
@150 mm ² /s	ASTM D4402	To be reported	220.9		
@180 mm ² /s	ASTM D4402	To be reported	74.4		
PG- (7)	KSF 2389	64	64		
PG-	KSF 2389	-22	-22		
at 64 G*/sin)	KSF 2389		1.14		
가 at 64 G*/sin)	KSF 2389		2.33		
at 25 (G* .sin)	KSF 2389		2956		
m at -12	KS F 2390		0.328		
at -12	KS F 2390		128.6		

최명수

