

	AP-5 PG 64-22		1621		2026-03-12 16:28
	520D122		RT2616214771		2026-02-26 04:00

, @15 kg/m <sup>3</sup>	KSM 2002	1000	1040	
(15 ) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	342	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.0	
가 ( (%) ) %	KSM 2252	55	67	
%	KSM 2252	110	102	
(25 )	KSM 2252	50 ~ 80	69	
가 mass%	KSM 2201	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	47.0	
@120 mm <sup>2</sup> /s	ASTM D4402	To be reported	1004.9	
@135 mm <sup>2</sup> /s	ASTM D4402		453.3	
@150 mm <sup>2</sup> /s	ASTM D4402	To be reported	229.4	
@180 mm <sup>2</sup> /s	ASTM D4402	To be reported	76.7	
PG- (7 )	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	
at 64 G*/sin )	KSF 2389		1.18	
가 at 64 G*/sin )	KSF 2389		2.27	
at 25 (G* .sin )	KSF 2389		3096	
m at -12	KS F 2390		0.329	
at -12	KS F 2390		142.8	

최명수

