

	AP-5 PG 64-22		1621		2024-08-02 08:34
	520D121		RT2416214616		2024-07-30 22:00

, @15 kg/m <sup>3</sup>	KSM 2002	1000	1043		
(15 ) cm	KSM 2254	100	140+		
,COC	KSM 2010	260	356		
FOAM ON HEAT,180	KSM 2201	NONE	NONE		
Loss on Heating wt%	KSM 2258	0.6	0.0		
가 ( ( % ) ) %	KSM 2252	55	70		
%	KSM 2252	110	110		
(25 )	KSM 2252	50 ~ 80	69		
가 mass%	KSM 2202-2	99.0	99.9		
	KSM 2250	44.0 ~ 52.0	47.5		
@120 mm <sup>2</sup> /s	ASTM D4402	To be reported	1028.9		
@135 mm <sup>2</sup> /s	ASTM D4402		458.1		
@150 mm <sup>2</sup> /s	ASTM D4402	To be reported	229.4		
@180 mm <sup>2</sup> /s	ASTM D4402	To be reported	75.7		
PG- (7 )	KSF 2389	64	64		
PG-	KSF 2389	-22	-22		

K. W. Hwang

